

EMS-TM-G10

Thermal grease, 1.0 W/m·K, 1 kg can and syringe

Non-curing thermal paste for the TIM2 plane, lid or heat-sink base to cold plate.

Non-curing thermal grease at 1.0 W/m·K, applied at a 0.05 mm minimum bond line. Apparent thermal impedance is 0.060 °C·in²/W (max) at 30 psi, measured by ASTM D5470 with both the test pressure and the thickness travelling with the figure. The failure it is selected against is pump-out: CTE mismatch between lid and cold plate displaces the paste over thousands of thermal cycles, and the grade stays correct on a flat interface with hard stops that set the bond line.

ORDERING INFORMATION

Part number	EMS-TM-G10
Thermal conductivity (through-plane)	1.0 W/m·K
Thermal impedance at 30 psi	0.060 °C·in²/W (max) at 30 psi
Minimum interface thickness	0.05 mm
Packaging	1 kg can; syringe for field rework
Ladder position	class band 0.015–0.060 °C·in²/W
Silicone content	Silicone-free grade quoted against drawing
Sample lead time	5–10 working days

THERMAL PERFORMANCE

Parameter	Value	Notes
Model code	EMS-TM-G10	Ladder position: class band 0.015–0.060 °C·in²/W.
Thermal conductivity, through-plane	1.0 W/m·K	ASTM D5470 three-point regression. Through-plane figure; comparable with pad and phase-change figures and never published without its pressure and thickness. ASTM D5470 measures apparent thermal impedance at a controlled pressure and thickness; intrinsic conductivity comes from repeating the measurement at several thicknesses and regressing the results, where the intercept is contact resistance and the slope gives the conductivity. A conductivity figure without its pressure and thickness is not a specification.
Thermal impedance at 30 psi	0.060 °C·in²/W (max) at 30 psi	Ladder target rather than a published figure: the datasheet renders the delivered batch impedance at 30 psi. The test pressure is the stated 30 psi; the thickness of the delivered batch is printed with the figure.
Thickness of the impedance figure	Printed with the figure on the datasheet	ASTM D5470 impedance depends on the bond line. The thickness behind the figure is stated with it, because the same grade publishes different impedance bands at different thicknesses.

Parameter	Value	Notes
Minimum interface thickness (bond line)	0.05 mm	Minimum interface thickness of the anchor grade across the ladder. A paste wets micro-gaps in a thin bond line; it does not bridge a gap. If assembly pressure or gap tolerance is uncontrolled, bond line varies across the part and impedance varies with it.
Two grades a factor of 2 apart in W/m-K	Far closer than a factor of 2 apart in impedance	Impedance at one bond line separates grades less than the conductivity column suggests, which is why the impedance row carries the same weight as the conductivity row.
Operating temperature range	-50 °C to +150 °C	Ladder range, bracketed by IEC 60068-2-14. A ceiling is a grade decision: a loop that runs hot removes the pad class before the conductivity comparison starts.
Thermal weight loss, 125 °C / 48 h	Issued with the datasheet for the delivered grade	No thermal weight-loss figure is published for this grade; the delivered grade's measured figure is issued with its datasheet.
Pre-heating before use	Confirmed per grade on the datasheet	The anchor grade is published with no pre-heating before use and no overflow up to 150 °C.
Pump-out resistance	Not published as a figure for this grade	Pump-out from CTE mismatch over thousands of thermal cycles is the dominant grease failure mode. The published selection warning asks the buyer to confirm pump-out risk, thermal cycling, storage and re-assembly. Countermeasures are a phase change material that softens in place or a cured pad.

PHYSICAL, COMPLIANCE AND PACKAGING

Parameter	Value	Notes
Density	Issued with the datasheet for the delivered grade	No density is published for this grade; the delivered grade's figure is issued with its datasheet.
Viscosity at 25 °C	Issued with the datasheet for the delivered grade	No viscosity is published for this grade; the delivered grade's figure is issued with its datasheet, Brookfield RVF, #7 spindle.
RoHS	Declared to the RoHS 2011/65/EU restricted-substance list	RoHS restricts ten substances at 0.1 % by weight per homogeneous material, with cadmium the exception at 0.01 %. Method IEC 62321. Published as the requirement the grade is built to, not as an approval held. Certification and standard designations are named only. No certificate, registration, patent or file number is published, and no third-party approval document is in hand for a model in this family.
Halogen content	Reported per delivered batch	Method EN 14582. No acceptance threshold is published here; the limit is set by the buyer's specification and the batch report is issued with the datasheet.

Parameter	Value	Notes
REACH	SVHC screen against the current candidate list	Method EN 14372. The 2025 REACH SVHC candidate list runs to more than 240 substances and includes three silicones: D4 (octamethylcyclotetrasiloxane), D5 (decamethylcyclopentasiloxane) and D6 (dodecamethylcyclohexasiloxane). Certification and standard designations are named only. No certificate, registration, patent or file number is published, and no third-party approval document is in hand for a model in this family.
Silicone content	Silicone-free grade quoted against drawing	Silicone oil does not stay in the bond line. The stocked silicone-free grade sits in the pad ladder at 2.0 W/m·K, 45–55 Shore 00, 2.5 g/cc.
Shelf life	Issued with the datasheet for the delivered grade	No shelf life is published for this grade; the delivered grade's figure is issued with its datasheet.
Packaging and storage	1 kg can · syringe	1 kg cans and syringes ship from stock; storage temperature per the safety data sheet. Samples ship in 5–10 working days.
Standards applied	ASTM D5470 · ASTM D792 · IEC 62321 · EN 14582 · EN 14372 · IEC 60068-2-14	Standard designations are named. Certification and standard designations are named only. No certificate, registration, patent or file number is published, and no third-party approval document is in hand for a model in this family.

APPLICATIONS

- Flat interfaces with hard stops that set the bond line
- Lid or heat-sink base to cold plate on a machined surface
- Stencil printing, screen printing or syringe dispensing
- Field rework where a cured pad cannot be positioned

COMPATIBLE WITH

- EMS-TM-P series gap filler pads where the gap is 1.0 mm or more
- EMS-TM-PC series phase change pads where thermal cycling drives pump-out
- EMS-TM-GR series graphene pads where through-plane conductivity above the grease band is required
- Stencil, screen-print and syringe dispensing equipment

NOT THE RIGHT PART WHERE

- The gap is above the bond line a paste is designed for; a paste does not bridge a gap
- The interface has to isolate: no dielectric breakdown or dielectric-constant figure is published for grease, so the answer is a pad at 5.0 kV/mm or more by ASTM D149, or an insulator film
- Thermal cycling is severe and the assembly cannot hold a hard stop; a phase change pad or a cured pad is the grade decision

MODEL LADDER — THERMAL GREASE

Parameter	Value	Notes
EMS-TM-G10	1.0 W/m·K · 0.060 °C·in²/W (max) at 30 psi	Ladder target, class band
EMS-TM-G20	2.0 W/m·K · 0.050 °C·in²/W (max) at 30 psi	Ladder target
EMS-TM-G30	3.0 W/m·K · 0.030 °C·in²/W (max) at 30 psi	Ladder target

Parameter	Value	Notes
EMS-TM-G35	3.5 W/m·K · 0.020 °C·in²/W at 30 psi	Published anchor model
EMS-TM-G50	5.0 W/m·K · 0.015 °C·in²/W at 30 psi	Published series minimum
EMS-TM-G60	6.0 W/m·K · 0.015 °C·in²/W (max) at 30 psi	Ladder target, premium class

CLASS CEILINGS FOR COMPARISON

Parameter	Value	Notes
Thermal grease	-50 °C to +150 °C	This ladder
Phase change	-40 °C to +125 °C	EMS-TM-PC series
Gap filler pad, 7.5 W/m·K	-65 °C to +125 °C	EMS-TM-P75-20
Gap filler pad, 5.0 W/m·K	-40 °C to +150 °C	EMS-TM-P50 series
Published class range for grease	1.0 W/m·K to 8.5 W/m·K	This ladder stops at 6.0 W/m·K, where only impedance at pressure separates grades

NOTES

- Thermal impedance is published with its test pressure and its thickness. Thermal conductivity never appears alone on this datasheet.
- Ladder targets are marked as such in the note column: where a figure is a ladder target rather than a published figure, the datasheet renders the delivered batch figure at the stated pressure.
- No electrical isolation row appears on a grease datasheet, because no dielectric breakdown or dielectric-constant figure is published for grease. Isolation is routed to the pad family: 5.0 kV/mm or more by ASTM D149 on the 5.0 W/m·K pad grade, or an insulator film.
- Where the figure you need is not on the datasheet, it is measured on the delivered batch and added to it.
- Scope: the TIM2 plane, lid or heat-sink base to cold plate and cold plate to manifold or rail. No coolant distribution units and no cold plates are supplied.
- Supplied by EMS-Trade Cooling, a Shenzhen trading house that integrates, inspects, stocks and ships. Die-cutting runs to the supplied drawing with a first-article inspection record per order. No manufacturing of this item is claimed.

Full specification sheet and current pricing EMS-Trade Cooling · ems-cool.com Typical lead time confirmed on order acknowledgement.	EMS-TM-G10 Rev. A 2026-09-19
---	---